L'ANTIC COLONIAL

Model: LINKFLOOR FEUDAL BROWN

Codes: 100298311 Group: G-224

Format: 22,8X152X0,5CM



| | | CC | OMPOSITION | |
|--|---------|------|------------|------------------------------|
| | | Size | Material | Type of material |
| | Layer 1 | 0.5 | Wear layer | Use layer with PU protection |
| | Layer 2 | 0.1 | Vinyl | decorative film |
| | Layer 3 | 3.4 | SPC | SPC core |
| | Layer 4 | 1.0 | IXPE | Foam |

FEATURES




Imitates the surface of wood











Squareness of the item (q)

Difference in height among items

There are consistent color changes between pieces.



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



5 year warranty for commercial use valid for vinyl materials that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with ISO 10582.



Is suitable for installing on water radiant heating



It is a quick and easy installation system. Adjust the slat to be installed lengthwise to the one already placed and tap it lightly with a rubber hammer and block. It is just as easy to uninstall, which allows it to be quickly dismantled.







LINKELOOR FELIDAL BROWN

L'ANTIC COLONIAL

| LABORATORY TESTS | | | | | | | |
|---|---|----------------------|--|--|--|--|--|
| Commercial area class | 33 | EN 10582* | | | | | |
| Slip resistance (r) | R-10 | DIN 51130* | | | | | |
| Abrasion resistance | CLASE T | EN 660-1,2* | | | | | |
| Impact resistance | PASS | EN 438-2* | | | | | |
| Swelling in thickness | 0.16 % | ISO 24336* | | | | | |
| Dimensional stability | LD: 0.04%/MD:-0.2% | ISO 23999* | | | | | |
| Resistance to microscratching | MSR-A1/MSR-B1 | EN 16094* | | | | | |
| Formaldehyde emissions | E1 | EN 717-2* | | | | | |
| Slip resistance (pendulum-wet) | CL 2 (41) | UNE 41901* | | | | | |
| Tensile strength of joints | Longitudinal=4.4 kN/m; Transversal=4.3 kN/m | ISO 24334* | | | | | |
| Fire resistance | Bfl-S1 | EN 13501* | | | | | |
| Evaluation of propensity to accumulation of electrostatic charges | 0.4 KV | EN 14021/ EN 1815* | | | | | |
| Heat resistance | 0.030 M2*K/W | UNE-EN 12667:2002* | | | | | |
| Thermal conductivity | 0.126 W/(m.k) W/M*K | UNE-EN 12667:2002* | | | | | |
| Uv light fastness | >Grado 6 | ISO 105* | | | | | |
| Curvature | 0.11 MM | ISO 23999* | | | | | |
| Acoustic insulation | IIC=56 dB;STC=50 dB ; ΔIIC=23 dB | ASTM E90; ASTM E492* | | | | | |
| Dynamic coefficient of friction | 0.47 | ANSI 137.1* | | | | | |
| Resistance to chemicals | PASS (CLASE 0) | ISO 26987* | | | | | |
| Private area class | 23 | EN 10582* | | | | | |
| Slip resistance (pendulum-dry) | CL 3 (80) | UNE 41902* | | | | | |

| | PACKING |
|------------------------------|-------------------|
| Sales units per box | 2.772476 M2/BOX |
| Sales units per pallet | 133.078855 M2/PAL |
| Sales units per unit | 0.34656 M2/PIECE |
| Sale unit | M2 |
| Base unit | ST |
| Sales units per square meter | 1 M2 |
| Net weight | 8.904675 KG/M2 |
| Gross weight | 9.268249 KG/M2 |

| SPECIAL PIECES | | | | | | | | | |
|----------------|---------------------------------------|-------|---------------|-----------------|----------------|-----|------------|----------------|----------------|
| SAP | Description | Group | Boxes | Pallet | Units | SKU | Basic Unit | Net Weight | Gross weight |
| 100312756 | MAMPER LINKFLOOR FEUDAL BROWN 7X120 | G-163 | 2 PIECES/BOX | 200 PIECES/PAL | 11.9 PIECES/M2 | - | = | 1.58 KG/PIECES | 1.64 KG/PIECES |
| 100312761 | PERFIL ADH LINKFLOOR FEUDAL BROWN 3,5 | G-155 | 20 PIECES/BOX | 1000 PIECES/PAL | 9.26 PIECES/M2 | - | - | 0.77 KG/PIECES | 0.8 KG/PIECES |
| 100312757 | ZOCALO LINKFLOOR FEUDAL BROWN 8X220 | G-121 | 14 PIECES/BOX | 560 PIECES/PAL | 5.68 PIECES/M2 | - | - | 1.33 KG/PIECES | 1.38 KG/PIECES |





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

08/06/2023